




HINDUSTAN NYLONS

PTFE: Tough Polymer For Tough Environment

TECHNICAL DATA SHEET

Grade No. HN-GL5-M5-F

5% Glass + 5% MoS2 Filled PTFE



Products : Moulded Rods, Moulded Bushes, Moulded Sheets, Skived Sheets & Machined Components

STANDARD :- ASTM-D-4745, Type I, Grade 4, Class A

Sr. No.	Parameter	Standard	Value
1	Colour	Visual	Light Grey
2	Density	ASTM-D-792	2.2~2.24 gm/cc
3	Tensile Strength	ASTM-D-638	175~250 Kg/cm ²
4	Elongation	ASTM-D-638	175~225 %
5a	Compressive Strength at 1% Deformation	ASTM-D-695	50~60 Kg/cm ²
5b	Compressive Strength at 10% Deformation	ASTM-D-695	160~180 Kg/cm ²
6	Coefficient of Friction	-	-
A	Static	ASTM-D-1894	0.055
B	Dynamic		0.050
7	Hardness	ASTM-D-2240	55~60 Shore D
8	Service Temperature	ASTM-D-648	- 200 ~ + 250°C
9	Water Absorption	ASTM-D-570	< 0.01 %
10	Dielectric Strength	ASTM-D-149	12~14 Kv/mm
11	Service Conditions (Properties)	<ul style="list-style-type: none"> • High compressive strength • Excellent chemical resistance • Improved wear resistance under load & permanent deformation • Improved frictional properties 	
12	Applications	Sealing Ring	