

Huntsman Advanced Materials Americas Inc.
5121 San Fernando Road West
Los Angeles, CA 90039
818.247.6210

Customer Service Hotline: 800.367.8793
Customer Service Faxline: 517.351.6255
Technical Inquiries: 800.817.8260



website: www.araldite.com
e-mail: adhesives_group@huntsman.com

Product Data

ARALDITE® AW 106 Resin Hardener HV 953U MULTI-PURPOSE EPOXY ADHESIVE

DESCRIPTION:	Araldite AW 106 resin/Hardener HV 953U epoxy adhesive is a multi-purpose, viscous material that is suitable for bonding a variety of materials including metal, ceramic, and wood. The electrically insulating adhesive is easy to apply either manually by spatula and stiff brush or mechanically with meter/mix and coating equipment. Araldite AW 106 resin/Hardener HV 953U epoxy adhesive cures at temperatures from 68°F (20°C) to 356°F (180°C) with no release of volatile constituents.
---------------------	---

APPLICATIONS:	• Metal • Ceramics • Wood • Vulcanized Rubber • Foams • Plastics
----------------------	--

ADVANTAGES:	• Long open time • High shear and peel strength • Easy to apply • Good resistance to static and dynamic loads • Electrically insulating
--------------------	---

TYPICAL PROPERTIES:	<u>Property</u>	<u>Test Method</u>	<u>Test Values⁽¹⁾</u>	
			<u>Resin</u>	<u>Hardener</u>
	Color/appearance	Visual	Creamy, viscous/liquid	Amber Liquid
	Specific Gravity	ASTM D-792	1.17	0.92
	Viscosity (cP) @ 77°F (25°C)	ASTM D-2393	50,000	35,000

TYPICAL MIXED PROPERTIES:	<u>Property</u>	<u>Test Method</u>	<u>Test Values⁽¹⁾</u>
	Reaction Ratio (by weight)		100R/80H
	Reaction Ratio (by volume)		100R/100H
	Pot Life, hours @ 77°F (25°C) (4.fl. oz. mass)	ASTM D-2471	2
	Mixed viscosity (cP) @ 77°F (25°C)	ASTM D-2393	45,000

¹Tested @ 77°F (25°C)

RECOMMENDED CURE SCHEDULES:	<u>Temperature</u>	<u>Handling Strength</u>	<u>Minimum Cure Time</u>
	68°F (20°C)	12 hours	15 hours
	77°F(25°C)	7 hours	12 hours
	104°F (40°C)	2 hours	3 hours
	158°F (70°C)	30 minutes	50 minutes
	212°F (100°C)	6 minutes	10 minutes
	302°F (150°C)	4 minutes	5 minutes

TYPICAL CURED PROPERTIES:

Application of Adhesive

The resin/hardener mix is applied with a spatula to the pretreated and dry joint surfaces.

A layer of adhesive 0.002 to 0.004-inches (0.05 to 0.10-mm) thick will normally impart the greatest lap shear strength to a joint.

The joint components should be assembled and clamped as soon as the adhesive has been applied. Even contact throughout suffices to ensure proper cure.

Standard Test Specimens

Unless otherwise stated, the figures given below were all determined by testing standard specimens made up by lap-jointing 4-inch x 1-inch x 0.06- inch (10-cm x 2.5-cm x 1.5-mm) strips of aluminum. The joint area was 0.5 x 1 inch (12.5 mm x 2.5 cm) in each case.

<u>Property</u>	<u>Test Method</u>	<u>Test Values⁽¹⁾</u>
Lap Shear Strength, psi (MPa)	ASTM D-1002	
<i>Effects of cure time and temperature</i>		

<u>Cure Temperature</u>	<u>Time</u>	
77°F (25°C)	8 hours	710 (4.9)
	15 hours	1990 (13.7)
	24 hours	2130 (14.7)
	72 hours	2280 (15.7)
	5 days	2560 (17.6)
158°F (70°C)	1 hour	3130 (21.5)
	2 hours	3410 (23.5)
	3 hours	3200 (22)
212°F (100°C)	10 minutes	3700 (25.5)
	20 minutes	3980 (27.4)
	30 minutes	4120 (28.4)
302°F (150°C)	5 minutes	4270 (29.4)
	10 minutes	4410 (30.4)
	20 minutes	4410 (30.4)

<u>Property</u>	<u>Test Method</u>
Lap Shear Strength, psi (MPa)	ASTM D-1002
<i>Effect of Test Temperature</i>	
(Load applied 10 minutes after specimens reach test temperature.)	

<u>Cure Cycle</u>	<u>Test Temp.</u>	
5 days @ 77°F (25°C)	-76°F (-60°C)	2840 (19.5)
	-4°F (-20°C)	2840 (19.5)
	68°F (20°C)	2560 (17.6)
	104°F (40°C)	1420 (9.8)
	140°F (60°C)	570 (3.9)
20 min @ 212°F (100°C)	-76°F (-60°C)	3560 (24.5)
	-4°F (-20°C)	3410 (23.5)
	68°F (20°C)	3980 (27.4)
	104°F (40°C)	1990 (13.7)
	140°F (60°C)	1000 (6.9)

¹Tested @ 77°F (25°C)

Property**Lap Shear Strength, psi (MPa)*****Effect of Immersion***

(Cure cycle 16 hours @ 104°F (40°C). Immersion for 90 days in media listed.)

<u>Media</u>	<u>Test Values⁽¹⁾</u>
Standard - As prepared	2560 (17.6)
Acetone (30 days)	570 (3.9)
Acetylene	430 (2.9)
Gasoline	2410 (16.6)
Ethyl Acetate (30 days)	570 (3.9)
Acetic Acid 10%	Degraded
Methanol	Degraded
Lubricating Oil - HD30	2560 (17.6)
Kerosene	Degraded
Trichloroethylene	Degraded
Water @ 68°F (20°C)	1420 (9.8)
Water @ 194°F (90°C)	430 (2.9)

Lap Shear Strength, psi (MPa)***Effect of Tropical Exposure***

(104°F/40°C at 92% R.H.)

<u>Cure Cycle</u>	<u>Exposure Time</u>	<u>Test Values⁽¹⁾</u>
16 hrs @ 104°F (40°C)	0 days	2560 (17.6)
	10 days	2560 (17.6)
	30 days	1710 (11.8)
	60 days	1560 (10.7)
	90 days	570 (3.9)
20 min @ 212°F (100°C)	0 days	3980 (27.4)
	10 days	2560 (17.6)
	30 days	1710 (11.8)
	60 days	1560 (10.7)
	90 days	1280 (8.8)

¹Tested @ 77°F (25°C)

Lap Shear Strength, psi (MPa)
Effect of Heat Aging
 (Cured 16 hours @ 104°F (40°C)).

Test Method
 ASTM D-1002

<u>Aging Temperature</u>	<u>Exposure Time</u>	<u>Test Values⁽¹⁾</u>
68°F (20°C)	0 days	2560 (17.6)
	1 years	2560 (17.6)
	2 years	2280 (15.7)
	3 years	1710 (11.8)
	4 years	1990 (13.7)
	5 year	1990 (13.7)
140°F (60°C)	3 days	2560 (17.6)
	10 days	2420 (16.6)
	30 days	2130 (14.7)
176°F (80°C)	3 days	2130 (14.7)
	10 days	2130 (14.7)
	30 days	2130 (14.7)
	60 days	2130 (14.7)
	1 year	1280 (8.8)
	2 years	710 (4.9)
	3 years	710 (4.9)
	4 years	430 (2.9)
	5 years	280 (1.9)
248°F (120°C)	3 days	2130 (14.7)
	10 days	2280 (15.7)
	30 days	2280 (15.7)
	60 days	2130 (14.7)

Property
Lap Shear Strength, psi (MPa)
Tested on Metal Substrates
 (Cured 20 min @ 212°F (100°C))

<u>Metal</u>	<u>Substrate Thickness</u> <u>(in./mm)</u>	<u>Test Values⁽¹⁾</u>
Carbon Steel	0.039/1.0	3840 (26.4)
Stainless Steel	0.039/1.0	3270 (22.5)
Galvanized Steel ²	0.06/1.5	1990 (13.7)
Copper	0.06/ 1.5	3270 (22.5)
Brass	0.06/ 1.5	2990 (20.6)

¹Tested @ 77°F (25°C)

²Surface degreased only, not roughened.

Property**Fatigue****Strength**

Tested using a load frequency of 90 Hz and a 1 inch (25 mm) joint overlap (Cured 20 min @ 212°F (100°C))

Fatigue Limit Load

<u>% Static Shear Strength</u>	<u>Cycles to Failure⁽¹⁾</u>
50	10 ³ -10 ⁴
40	10 ⁴ -10 ⁵
30	10 ⁵ -10 ⁶
25	10 ⁵ -10 ⁶
20	10 ⁶ -10 ⁷
15	10 ⁷

Property**Test Method****Test Values⁽¹⁾**

Ultimate Tensile Strength, psi (MPa)	ASTM D-638	4800 (33)
Elongation, %	ASTM D-638	9
Tg per DMA, °F (°C)	ASTM D-4065	146 (63)
Hardness, Shore D	ASTM D-2240	80
Coefficient of Thermal Expansion 10 ⁻⁵ (in/in/°C)	ASTM E-831	8.5 x
Roller Peel Test, pli (N/mm)	ISO 4578	28 (4.9)

¹Tested @ 77°F (25°C)

Electrical Properties

Thermal Conductivity, W/mK	0.22
Surface Resistivity, ohms	1.2 E+16
Dielectric Strength, volt/mil	400
Volume Resistivity, ohms-cm	7.1 E+14
Dielectric Constant, at 50Hz/1KHz/10KHz	3.4/3.2/3.2
Loss Tangent, % at 50Hz/1KHz/10KHz	1.7/1.8/2.6

**STORAGE/
SHELF LIFE:**

Araldite epoxy adhesive components should be stored in their original, sealed containers at room temperature. When stored at temperatures from 59-77°F (15-25°C), the resin and hardener will remain in useable condition for 12 months from date of shipping from Huntsman.

CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to adhesives_group@huntsman.com.

FIRST AID!

Eyes and skin: Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation: Remove subject to fresh air.

Swallowing: Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

IMPORTANT LEGAL NOTICE:

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

WARRANTY: Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture.

DISCLAIMER AND LIMITATION OF LIABILITY: EXCEPT AS SET FORTH ABOVE, HUNTSMAN MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Huntsman neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE. Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Huntsman and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing DISCLAIMER AND LIMITATION OF LIABILITY supersedes Buyer's documents.

WARNING: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc.
Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.

Note: The information contained herein are typical values intended for reference and comparison purposes only. They should NOT be used as a basis for design specifications or quality control. All values at 23°C unless otherwise noted.